

GHP Non-Metal Reinforced Laminate

TECHNICAL DATA SHEET 132


Product Family - Laminates (Non-Metal Reinforced)

- GHP GTB with Plastic Insert
- · GHN TG-337 with Plastic Insert
- GHW GTB with Woven Glass Fiber Insert
- GRAFKOTE® GTB with Plastic Facing

· Glass-lined or low load flange equipment

- Steam traps

Heat exchangers




Applications


- Valves
- Pumps
- Pipe Flanges/ ASME/ API/ DIN flanges
- Compressors

LOAD BEARING ABILITY

High Temperature Creep Relaxation (BS1-F125)



LEAK RATE VS CLAMPING LOAD Sealability @ Room Temperature & 400°C



www.neograf.com www.grafoil.com

GRAFOIL® GHP NON-METAL REINFORCED LAMINATE

Advantages of GRAFOIL® GHP Non-Metal Reinforced Laminate

- Compatible with a wide range of chemicals
- Maximum continuous use temperature 400°C (750°F)
- · No shelf life
- Material availability in rolls allows for maximum material utilization
- · Cost effective

- Easily cut
- · Contains no hazardous materials
- · Robust enough for easy handleability and durability
- Superior to non-asbestos fiber sheet in every characteristic (Temp, Creep, Recovery and Sealability)

Typical Properties*

Certification	Certify to Grade
Tensile Strength	765 psi (5.3 MPa)
Sealability Method: Mod DIN 3535at 580 psi N2 at 32 MPa load	<1.5 ml/minfor 70 lb/ft³
Creep Relaxation Method: BSI-F125 at 6391 psi (44.1 MPa) load up to 400°C	<4%for 70 lb/ft³
Recovery after 5000 psi (35 MPa) load	14%
Compressibility at 5000 psi (35 MPa) load	44%
Bulk Density (Graphite)	70 lb/ft³ (1.12 g/cc)
Length	39.4" (1000 mm) 100' (30.5 m)
Width	39.4" (1000 mm)
Thickness of Laminate	0.032" (0.81 mm) 0.062" (1.57 mm)
CHARACTERISTIC	TYPICAL VALUE

Notes

^{*} Properties listed are typical and cannot be used as accept/reject specifications.

^{+1 (800) 253.8003 (}Toll-Free in USA) | +1 (216) 529.3777 (International) www.neograf.com | info@neograf.com