

GTA TG-312 Flexible Graphite

TECHNICAL DATA SHEET 619

Product Overview


GraFoil® GTA TG-312 flexible graphite is high-purity for use in applications that are sensitive to impurities.

Product Family - Single Layer Material (Service to 450°C)

- TG-411 - 99.998% Graphite
- **TG-312 - Non-Nuclear 99.8% Graphite**
- GTA - Nuclear 99.8% Graphite
- GTC - 97% Graphite

Applications

- Furnace Process Liners
- Semiconductor Process Liners
- Industrial Press Pads



Typical Properties*

CHARACTERISTICS

TYPICAL VALUE

Thickness	0.003" (0.08 mm) 0.010" (0.25 mm)
Width	24" (610 mm)
Length	100' (30.5 m)
Bulk Density	70 lb/ft ³ (1.12 g/cc)
Ash Content	0.2%
Carbon Content	99.8%
Leachable Chloride	<10 ppm
Sulfur Content	1000 ppm
Total Chlorides	<50 ppm
Total Fluorides	<10 ppm
Total Halogens	40 ppm
Total Nitrates	10 ppm
Total Nitrites	1 ppm
Mercury (Hg)	<0.5 ppm
Phosphorus	30 ppm
Aluminum (Al)	15 ppm
Copper (Cu)	<10 ppm
Temperature Use Range (in air)	-400°F to 850°F and (-240°C to 450°C)
Temperature Use Range (in vacuum or reducing environments)	-400°F to 5400°F (-240°C to 3000°C)
Certification	Certify to Grade

* Properties listed are typical and cannot be used as accept/reject specifications.

LEAD. CREATE. CONNECT.

+1 (800) 253.8003 (Toll-Free in USA) | +1 (216) 529.3777 (International)
www.neograf.com | info@neograf.com

©2024 NeoGraf Solutions, LLC (NGS). This information is based on data believed to be reliable, but NeoGraf Solutions, LLC makes no warranties, express or implied, as to its accuracy and assumes no liability arising out of its use. The data listed falls within the normal range of product properties but should not be used to establish specification limits or used alone as the basis of design. NeoGraf Solutions, LLC liability to purchasers is expressly limited to the terms and conditions of sale. eGraf®, Graf+®, GrafGuard®, GraFoil®, and GrafCell® are registered trademarks of NeoGraf Solutions, LLC. NeoNxGen™, SpreaderShield™, HiTherm™, Graf-X™, Graf-M™ are trademarks of NeoGraf Solutions, LLC. These trademarks are not a comprehensive listing of all NeoGraf products or trademarks used or owned by NeoGraf Solutions, LLC. eGraf®, NeoNxGen™, SpreaderShield™, HiTherm™, Graf+®, Graf-X™, Graf-M™, GrafGuard®, GraFoil®, and GrafCell® products, materials, and processes are covered by several US and foreign patents. For patent information www.neograf.com.